



## DESCRIPTION

## THERMALLY SENSITIVE RECORDING MEDIUM

## FIELD OF THE INVENTION

The present invention relates to a thermally sensitive recording medium which ~~utilize color developing~~ utilizes a color-developing reaction of a colorless basic leuco dye with a ~~color-developing~~ color-developing agent.

~~BACK-GROUND~~ BACKGROUND OF THE INVENTION

In general, a thermally sensitive recording medium is prepared by pulverizing a colorless or pale colored basic leuco dye and a ~~color-developing~~ color-developing agent to fine particles respectively, mixing these two fine particles with additives such as a binder, a filler, a sensitizer, a slipping agent or others and ~~form~~ forming a coating, then ~~by~~ coating the obtained coating on a substrate such as paper, synthetic paper or plastics. ~~Prepared~~ The prepared thermally sensitive recording medium develops color by an instant chemical reaction by heating with a thermal head, a hot stamp, a thermal pen or laser and a recorded image can be obtained. A thermally sensitive recording medium is widely applied in a facsimile, a printer of computer, a bending machine for a ticket and a recorder of various measuring ~~instrument~~ instruments. Recently, recording ~~equipments~~ equipment ~~are becoming~~ has begun to have more diversity and high quality and, along with said tendency, ~~high-speed~~ high-speed printing and ~~high-speed~~ high-speed formation of ~~image~~ images are becoming possible, and an excellent quality for the recording density of a thermally sensitive recording medium is required. Further, along with the diversibility of usage, the performance of a high quality recorded image is required in all regions from a lower density to a high density.

As a method ~~to satisfy above mentioned~~ of satisfying the above-mentioned requirements, a method ~~to improve~~ of improving

the surface smoothness of a thermally sensitive recording medium by a super calendar is ordinary carried out, however, a printed image of sufficient quality ~~can not~~cannot always be obtained. Further, it is well known that the uniform coating of an undercoating layer is necessary for formation of ~~high quality~~a high-quality printed image, and a method ~~to improve of~~improving the smoothness of the undercoating layer, for example, using a super calendar is known. Still further, for the purpose ~~to provide of~~providing a thermally sensitive recording medium which is superior in dot ~~reappearance ability~~reappearance, for example, a method to accumulate first and second intermediate layers is proposed in patent document 1.

Patent document 1; JP 2000-108518 publication

#### DISCLOSURE OF THE INVENTION

However, by the method using a super calendar, a porous feature of the undercoating layer is hurt by the calendar pressure ~~and, an~~ adiabatic ability is lost, and the sensitivity is deteriorated. Further, a method ~~to accumulate of~~accumulating a first intermediate layer and a second intermediate layer is disadvantageous from a manufacturing view point, because the process becomes more complicated. The object of the present invention is to provide a thermally sensitive recording medium ~~characterizing to have~~characterized in having a high recording sensitivity and to be able to obtain high quality recorded ~~image~~images without causing the above problems.

~~Above~~The above object can be accomplished by a thermally sensitive recording medium comprising an undercoating layer containing a pigment and a binder as main components and a thermally sensitive ~~color-developing~~color-developing layer containing a colorless or ~~pale-colored~~pale-colored basic leuco dye and a ~~color-developing~~color-developing agent which develops a color by reacting with said basic leuco dye as main components on a substrate, wherein said undercoating layer

contains a water-retention agent and a pigment whose ~~oil~~  
~~absorbing~~oil-absorbing capacity (JIS K 5105) is from 80cc/100g  
to 120cc/100g as a pigment, further~~-solid~~, the solids  
concentration of a coating for the undercoating layer is from  
25% to 45% and the dynamic water-retention capacity (Water  
retention measured with AA-GWR) is 350g/m<sup>2</sup> or less. ~~And it~~As is  
well known in the art, AA-GWR water retention measurement is  
based on the pressure filtration of coatings under an  
externally applied air pressure of a certain time period and  
utilizes gravimetric determination of an aqueous phase  
penetrating through a filter and absorbed by a paper sample.  
It is desirable to use sodium alginate as a water-retention  
agent ~~tefor~~ for the thermally sensitive recording medium.

The present invention is made by finding out that the  
penetrating condition of a coating fluid at the coating  
process (hereinafter shortened as a coating) ~~tefor~~ for a paper  
becomes an important factor for a coating aptitude and a  
quality. In particular, at a contact type coating system, such  
as blade coating, is characterized ~~te push~~ by pushing a coating  
~~in into a paper, therefore paper.~~ Therefore by evaluating the  
penetrating condition of the coating into the paper at a  
pressed condition, the coating aptitude of the coating can be  
known. Further the present invention ~~is paying~~ pays attention  
to a relationship between the solid concentration and dynamic  
water-retention capacity (Water retention measured with AA-  
GWR) of a coating liquid for an undercoating layer, and it is  
important that the solid concentration is from 25% to 45% and  
dynamic water-retention capacity (Water retention measured  
with AA-GWR) is 350g/m<sup>2</sup> or less.

#### DESCRIPTION OF THE PREFERRED EMBODYMENT

The preferred embodiment of the present invention will be  
illustrated as follows.

An undercoating layer of the present invention contains a  
pigment and a binder as main components, and solid  
concentration of a coating liquid is from 25% to 45%,

desirably from 30% to 40%, and dynamic water-retention capacity (Water retention measured with AA-GWR) of a coating liquid is 350g/m<sup>2</sup> or less, desirably is 300g/m<sup>2</sup> or less.

Dynamic water-retention capacity used in the present invention is one of the methods to evaluate the characteristics of a coating which measures the penetration of the coating ~~teinto~~ into a paper at a certain pressure and time and is indicated by g/m<sup>2</sup> unit. When this value is small, it means that a coating is hard to penetrate into a paper and more coating remains on the surface of a paper, and the coated quality becomes better. ~~And when solid~~ When the solids concentration of the coating liquid is higher, the water content is small and the water-retention ability ~~deteriorated~~ deteriorates so that the coating aptitude becomes bad, while, when the concentration of the coating liquid is lower, the water content ~~becomes large~~ and water-retention ability ~~becomes~~ become large, however, the viscosity of the coating liquid ~~is deteriorated~~ deteriorates and the coating aptitude becomes bad. On the ~~contrary~~ other hand, in the present invention, an excellent coating aptitude can be obtained by maintaining the concentration of a coating liquid in a range from 25% to 45% and the dynamic water-retention capacity (Water retention measured with AA-GWR) to 350g/m<sup>2</sup> or less. Wherein, the dynamic water-retention capacity (Water retention measured with AA-GWR) of the present invention is measured ~~in at~~ at the condition conditions of 23°C temperature, 0.5MPa pressure, for 40 minutes and 20ml of liquid quantity using 1 sheet of filter paper.

~~Solid~~ The solids concentration and dynamic water-retention capacity of a coating liquid can be adjusted by ~~kind~~ the kind and adding quantity of a binder such as starch, polyvinylalcohol or carboxymethylcellulose, however, the viscosity under a high shearing speed can be easily elevated and a coating aptitude and quality changes. Therefore, the addition of a water-retention agent is most effective.

A The kind of ~~a~~ water-retention agent is not particularly

restricted, and it is possible to adjust the features of water-retention ability or viscosity to the aptitude region of the present invention by properly controlling the adding amount. As a water-retention agent, an acrylic or ~~ana~~ urethane synthetic water-retention agent, or sodium alginate can be mentioned. Especially, when sodium alginate is contained, good water-retention ability can be obtained by a small adding quantity, and by suppressing the penetration of a coating in a thermally sensitive recording medium which is excellent in recording sensitivity and has good quality of image can be obtained. Further, among sodium alginates, the use of a higher viscosity one is more desirable. In a case of sodium alginate of a lower viscosity, it is necessary to add a large quantity to perform a good water-retention ability, however, the use of large quantity has a tendency to deteriorate a recording sensitivity. In the present invention, sodium alginate whose Brookfield viscosity (B viscosity) of a 1% aqueous solution at 25°C is 100mPa·s or more is desirable, preferably 500mPa·s or more is more desirable.

Further, it is desirable to use a water-retention agent by 0.01-1 weight parts to 100 weight parts of a pigment. A water-retention agent to be used in the present invention is considered to have an effect ~~to improve~~ of improving the water-retention ability of a coating liquid and to prevent the penetration of a coating. When the blending parts of the water-retention agent is too small, a sufficient water-retention ability ~~can not~~ cannot be obtained, and when the blending parts is too large, coating work becomes impossible because the viscosity becomes too high. Accordingly, in the present invention, it is desirable to contain 0.01-1 weight parts of the water-retention agent, especially sodium alginate to 100 weight parts of the pigment. ~~More~~ A more desirable amount is 0.01-0.8 weight parts to 100 weight parts of the pigment, ~~Furthermore~~ and a furthermore desirable amount is 0.01-0.6 weight parts.

In the present invention, the reason why the excellent

effect can be obtained is considered as follows. As one reason why the quality of the printed image deteriorates, a low concentration of ~~solid~~the solids part of a coating liquid for an undercoat layer in a thermally sensitive recording medium can be mentioned. Although, depending on the materials to be used, aiming to obtain a good quality or dispersability of a coating, compared with a case that the ~~solid~~solids concentration of a coating for a coated layer of ordinary coating paper for printing is 60-70%, sometimes the ~~solid~~solids concentration of the coating for an undercoating layer is set to be approximately 40% or less. In said case, a binder component has a tendency to migrate (transfer) easily to lower part, accordingly, the distribution of the binder and orientation of the pigment in the coated layer become uneven. ~~And when~~When a thermally sensitive recording layer is formed on it, thermal energy is not transmitted uniformly and causes an uneven problem of ~~dot~~the dots, therefore, the quality of the recorded image is deteriorated. On the ~~contrary~~other hand, in the present invention, by blending a water-retention agent, especially, sodium alginate, to a coating, improvement of the water-retention ability and fluidity can be ~~expected~~, accordingly expected. Accordingly, migration of a binder is prevented and ~~an~~a uniform coated layer can be obtained.

In the undercoating layer of the present invention, ~~starch~~starches and derivatives, modified ~~starch~~starches and derivatives, ~~polyvinylalcohol~~polyvinylalcohols and derivatives, modified polyvinyl ~~alcohol~~alcohols and derivatives, methylcellulose, carboxymethylcellulose, ~~water soluble polymer~~water-soluble polymers such as styrene-maleic anhydride, ~~emulsion~~emulsions of synthetic ~~resin~~resins such as a styrene-butadiene copolymer, acrylic acid copolymer, urethane resin or vinyl acetate can be added.

Formation of an undercoating layer can be easily carried out by coating a coating liquid over a substrate such as paper, reclaimed paper, plastic film or synthetic paper using an ordinary coating machine by 1-15g/m<sup>2</sup> coating amount. As a

coating method, an air knife method, blade method, gravure method, roll coater method or curtain method can be mentioned and any kind of method can be used, however, from the view point that coating by a high concentration is possible and a coating liquid does not penetrate easily into a substrate and a uniform layer can be formed, it is desirable to form an undercoating layer by a blade coater method.

As a pigment to be contained in the undercoating layer, a pigment whose ~~oil-absorbing~~ oil-absorbing capacity (JIS K 5105) is from 80cc/100g to 120cc/100g is preferably used and not restricted, however, as a kind of pigment, clay (kaolin), calcined clay (calcined kaolin), calcium carbonate, aluminum oxide, titanium dioxide, magnesium carbonate, amorphous silica or colloidal silica can be mentioned. In particular, calcined clay is most desirable, because a thermally sensitive recording medium which is well-balanced in recording sensitivity and quality of image can be obtained. By using the calcined clay, it is considered that sufficient adiabatic effect is provided and sensitivity is improved, further, since a binder is not absorbed by a pigment so much, a uniform coated layer is formed and an excellent quality of image can be obtained. In the meanwhile, when calcined clay is used, since the shape of calcined clay is flat, the fluidity of a coating is generally inferior compared with a coating containing calcium carbonate or others whose shape is spherical, further, since an OH group (hydroxyl group) of silanol does not exist on the surface because it is calcined, bonding with water becomes weak and ~~have it has~~ it has a tendency to deteriorate the water-retention ability of a coating liquid.

On the ~~contrary~~ other hand, in the present invention, by the effect of a water-retention agent, in particular, sodium alginate, in a case when calcined clay is used, the coating aptitude is improved. Compared with polyvinylalcohol or carboxy methylcellulose, sodium alginate is superior in adhesive uniformity of solution. Therefore, the protective colloid function becomes large and it is considered that this

characteristic acts effectively. To a coating liquid for an undercoating layer, a dispersing agent, wax, thicker, surfactant, ~~UV-absorbing~~UV-absorbing agent, antioxidant, ~~water repellent~~water-repellent agent or ~~oil-repellent~~oil-repellent agent can be added when a need is arisen.

It is desirable that the Brookfield viscosity (B viscosity) of a coating liquid for an undercoating layer at 25°C is 200-1500mPa·s. Further, it is desirable that the viscosity at shearing speed of  $4.0 \times 10^{-5} \text{sec}^{-1}$  -  $8.0 \times 10^{-5} \text{sec}^{-1}$  at 25°C (high shear viscosity) is 20-100mPa·s, more desirably is 30-50mPa·s. Said B viscosity is a viscosity corresponding to the shear when a coating liquid is supplied to a substrate by an applicator, while said high shear viscosity is a viscosity corresponding to the shear when a coating is scraped off from a substrate by a scraper.

When a coating liquid is supplied to a substrate by an applicator, if the coating does not have an adequate viscosity, the uniform supply of the coating liquid becomes difficult. For example, in a case when the viscosity of the coating is too low, a problem that the necessary coating amount ~~can not~~cannot be obtained is caused, because ~~pick-up~~the pick-up amount of the coating liquid by an applicator roll becomes small. On the ~~contrary~~other hand, when the viscosity of the coating liquid is too high, a problem may be caused in a ~~pump-up~~pump-up process.

In general, regarding a blade coater method such as bar blade, the formation of a stable (uniform) coated layer is not possible without adding pressure of a certain range. In the blade coater method, when the pressure to scrape off a coating is too low, uniform ~~scrapes~~scraping off of the coating is difficult and a uniform coated layer ~~can not~~cannot be formed, while when the pressure to scrape off a coating is too high, a problem that a substrate is broken is caused. Therefore, in the blade coater method, when the viscosity to the shear at the scraping off process is too small, the coating liquid is easily scraped off and a necessary coating amount ~~can~~



~~not~~cannot be obtained. In the meanwhile, when the high shear viscosity is too high, it is difficult to scrape off the coating to the aimed coating amount.

On the ~~contrary~~other hand, in the present invention, by using a coating which indicates the above viscosity, the migration of the coating ~~to~~into a substrate is prevented and a uniform coated layer with good covering ability is formed.

A thermally sensitive recording layer to be formed on an undercoating layer can be formed according to conventional well-known methods.

As a colorless or ~~pale-colored~~pale-colored basic leuco dye to be used ~~to~~with the thermally sensitive recording medium of the present invention, all ~~public-known~~publicly-known dyes which are well-known in conventional ~~pressure sensitive~~pressure-sensitive or ~~thermally sensitive~~thermally-sensitive recording paper ~~field~~fields can be used and are not restricted, however triphenylmethane compounds, fluorane compounds, fluorene compounds or divinyl compounds can be desirably used. Specific examples of a colorless or ~~pale-colored~~pale-colored basic leuco dye are shown below. These compounds can be used alone or can be used ~~together within~~combination.

<triphenyl methane leuco dye>

3,3'-bis(p-dimethylaminophenyl)-6-dimethylaminophthalide

{another name; Crystal Violet ~~Lacton~~Lactone} ,

3,3-bis(p-dimethylaminophenyl)phthalide

{another name is Malachite Green Lactone}

<Fluorane leuco dyes>

3-diethylamino-6-methylfluorane

3-diethylamino-6-methyl-7-anilinofluorane

3-diethylamino-6-methyl-7-(o,p-dimethylanilino)fluorane

3-dibutylamino-6-methyl-fluorane

3-dibutylamino-6-methyl-7-anilinofluorane

3-dibutylamino-6-methyl-7-(o,p-dimethylanilino)fluorane

3-dibutylamino-6-methyl-7-(o-chloroanilino)fluorane

3-dibutylamino-6-methyl-7-(p-chloroanilino) fluorane  
 3-dibutylamino-6-methyl-7-(o-fluoroanilino) fluorane  
 3-n-dipentylamino-6-methyl-7-anilinofluorane  
 3-(N-ethyl-N-isoamylamino)-6-methyl-7-anilinofluorane  
 3-(N-ethyl-N-isoamylamino)-6-chloro-7-anilinofluorane  
 3-cyclohexylamino-6-chlorofluorane  
 <divinyl leuco dyes>  
 3,3-bis-[2-(p-dimethylaminophenyl)-2-(p-methoxyphenyl)ethenyl]-4,5,6,7-tetrabromo phthalide  
 3,3-bis-[2-(p-dimethylaminophenyl)-2-(p-methoxyphenyl)ethenyl]-4,5,6,7-tetrachloro phthalide  
 3,3-bis-[1,1-bis(4-pyrrolidinophenyl)ethylene-2-yl]-4,5,6,7-tetrabromophthalide  
 3,3-bis-[1-(4-methoxyphenyl)-1-(4-pyrrolidinophenyl)ethylene-2-yl]-4,5,6,7-tetra chlorophthalide  
 <Others>  
 3-(4-diethylamino-2-ethoxyphenyl)-3-(1-ethyl-2-methylindol-3-yl)-4-azaphthalide  
 3-(4-diethylamino-2-ethoxyphenyl)-3-(1-octyl-2-methylindol-3-yl)-4-azaphthalide  
 3-(4-cyclohexylethylamino-2-methoxyphenyl)-3-(1-ethyl-2-methylindol-3-yl)-4-azaphthalide  
 3,3-bis(1-ethyl-2-methylindol-3-yl)phthalide  
 3,6-bis(diethylamino) fluorane-γ-(3'-nitro) anilinolactam  
 3,6-bis(diethylamino) fluorane-γ-(4'-nitro) anilinolactam  
 1,1-bis-[2',2',2'',2'''-tetrakis-(p-dimethylaminophenyl)-ethenyl]-2,2-dinitrilethane  
 1,1-bis-[2',2',2'',2'''-tetrakis-(p-dimethylaminophenyl)-ethenyl]-β-naphthoyl ethane  
 1,1-bis-[2',2',2'',2'''-tetrakis-(p-dimethylaminophenyl)-ethenyl]-2,2-diacetylene  
 bis-[2,2,2',2'-tetrakis-(p-dimethylaminophenyl)-ethenyl]-methylmalonic acid dimethyl ester.

As a ~~color developing~~color-developing agent to be used in the present invention, any kinds of ~~public~~publicly known ~~color~~

~~developing~~color-developing agent which makes a colorless or ~~pale-colored~~pale-colored basic leuco dye develop color is suitable. As a specific example, for example, bisphenol A, 4-hydroxybenzoic acid esters, 4-hydroxyphthalic acid diesters, phthalic acid monoesters, bis-(hydroxyphenyl)sulfides, 4-hydroxy phenylarylsulfones, 4-hydroxyphenylarylsulfonates, 1,3-di[2-(hydroxyl phenyl)-2-propyl]-benzenes, 4-hydroxybenzoiloxo benzoic acid esters or bisphenolsulfones disclosed in the JP H3-207688 publication or the JP H5-24366 publication can be mentioned.

Further, in a thermally sensitive recording medium of the present invention, a conventional sensitizer can be used ~~likely~~similar to the conventional thermally sensitive recording medium. As the specific example of the sensitizer, a fatty acid amide such as a stearic acid amide or parmitic acid amide, ethylenebisamide, montan wax, polyethylene wax, 1,2-di(3-methylphenoxy)ethane, p-benzylbiphenyl,  $\beta$ -benzyloxynaphthalene, 4-biphenyl-p-tolyl ether, m-terphenyl, 1,2-diphenoxyethane, dibenzyl oxalate, di(p-chlorobenzyl)oxalate, di(p-methylbenzyl)oxalate, dibenzylterephthalate, benzyl p-benzyloxybenzoate, di-p-tolylcarbonate, phenyl- $\alpha$ -naphthylcarbonate, 1,4-diethoxynaphthalene, phenyl 1-hydroxy-2-naphthoate, 4-(m-methylphenoxyethyl)biphenyl, 4,4'-ethylenedioxy-bis-dibenzylbenzoate, dibenzoyloxymethane, 1,2-di(3-methylphenoxy)ethylene, bis[2-(4-methoxy-phenoxy)ethyl]ether, methyl p-nitrobenzoate or phenyl p-toluenesulfonate can be mentioned, however, it is not restricted to these compounds. These sensitizers can be used alone or can be used ~~together~~ within combination.

Further, as an image stabilizer which displays resistance effect to oil of recorded image, 4,4'-butylidene(6-t-butyl-3-methylphenol), 2,2'-di-t-butyl-5,5'-dimethyl-4,4'-sulfonyldiphenol, 1,1,3-tris(2-methyl-4-hydroxy-5-cyclohexylphenyl)butane or

1,1,3-tris(2-methyl-4-hydroxy-5-t-butylphenyl)butane can be added.

Still further, a releasing agent such as a metal salt of fatty acid, a slipping agent such as waxes, ~~an UV-absorbing~~ a UV-absorbing agent such as benzophenones or ~~triazoles~~ triazoles, a ~~water-resistance~~ water-resistant agent such as ~~glyoxal~~ glyoxal, a dispersing agent, a defoaming agent, an antioxidant or a fluorescent dye can be used.

~~Kinds~~ The kind and amount of components, e.g. basic leuco dye, ~~color-developing~~ color-developing agent or others to be used in the thermally sensitive recording medium of the present invention are decided according to the required properties and recording aptitude and not restricted, however, in general, 0.5-10 parts of ~~color-developing~~ color-developing agent and 0.5-10 parts of filler to 1 part of the basic leuco dye are used.

~~Basic~~ The basic leuco dye, ~~color-developing~~ color-developing agent and other materials to be added by necessity are pulverized by a grinder such as a ball mill, attriter or sand grinder, or by means of an adequate emulsifying apparatus, until they are pulverized under several ~~micron~~ microns size, then ~~addis~~ added ~~an~~ an acrylic emulsion, colloidal silica and various additives according to the object, thus a coating is prepared. ~~Coating~~ The coating amount of a thermally sensitive recording layer is not particularly restricted, however, it preferably is in the range of 2-12g/m<sup>2</sup> by dry weight. The means for coating is not restricted and ~~public~~ publicly known conventional methods can be used, for example, an off machine coater with various ~~coater~~ coaters such as an air knife coater, a rod blade coater, a bill blade coater, a roll coater or a curtain coater or an on machine coater can be voluntarily chosen and used. Among these machines, a curtain coater process is desirable, because said process provides a good printed image.

As one of the ~~ground to deteriorate~~ grounds for a deteriorated printed image, the following reasoning can be

mentioned. When a thermally sensitive recording layer is formed on an undercoating layer by a blade coating method, which is a generally used method, the surface of the thermally sensitive recording layer becomes smooth by the scraping action of a blade, however, the surface of the undercoating layer is directly affected by the uneven surface of a substrate paper and is not so smooth compared with the surface of the thermally sensitive recording layer. Consequently, the thickness of the thermally sensitive recording layer becomes ~~inequal~~, unequal and the existing quantity of ~~color~~ developing the color-developing materials becomes different ~~by~~ from position to position. Therefore, when the thermal energy is ~~loaded~~ applied, the degree of the developed color becomes uneven, especially, in a case of high energy printing, the developed color becomes deeper at a thicker position and it is difficult to obtain an excellent quality in a printed image. On the contrary other hand, in a the case of a curtain coater method, a coating liquid is not scraped off and an outline coating is possible, that is, the thermally sensitive recording layer can be formed so as to go along with the outline of the undercoating layer. Therefore, the thickness of the thermally sensitive recording layer becomes even, so that the unevenness of the printing density may be prevented and the printed image can be improved.

The thermally sensitive recording medium of the present invention can provide an ~~over-coating~~ overcoating layer composed of a polymer on the thermally sensitive recording layer for the purpose ~~to improve~~ of improving the preservability, or can provide an undercoating layer composed of a polymer containing a filler under the thermally sensitive recording layer. On the opposite side of the substrate to the thermally sensitive layer, a ~~back-coat~~ backcoat layer can be provided for the purpose ~~to correct~~ of correcting the curling of the medium. Further, various ~~public~~ publicly-known ~~technique~~ techniques in the field of thermally sensitive recording ~~medium~~ mediums can be added, for example, ~~to~~

~~carry~~carrying out a smoothing treatment such as super ~~calendar~~calendaring after the coating process of each ~~layers~~layer.

As a substrate of the thermally sensitive recording medium of the present invention, paper, recycled paper, synthetic paper, film, plastic film, plastic foam film or non-woven cloth can be properly selected and used according to an use. ~~And a~~A composite sheet which is prepared by combining these substrates can be used as a substrate.

#### EXAMPLE

The thermally sensitive recording medium of the present invention will be illustrated ~~more actually~~ according to the Examples. In illustration, "parts" and "%" indicates "weight parts" and "weight %".

Solutions, dispersions or coating liquids are prepared as follows.

#### Example 1

~~Mixture~~A mixture of the following blending ratio is stirred and dispersed, and coating liquids for an undercoating layer are prepared ~~so as solid~~to have the solids concentration and dynamic water-retention capacity ~~to be as~~ indicated in Table 1.

U solution (coating for undercoating layer)

Calcined clay (product of Engelhard Co., Ltd., commodity name; Ansilex

90, <oil--absorbing capacity 90cc/100g>	100 parts
---	-----------

Styrene-butadiene copolymer latex	
-----------------------------------	--

( <del>solids</del> <u>solids</u> part 48%)	40 parts
---	----------

10% aqueous solution of polyvinylalcohol	30 parts
--	----------

2% aqueous solution of sodium alginate	5 parts
--	---------

(viscosity of 1% aqueous solution: 600-900mPa·s, product of Kelco Co., Ltd., commodity name; Kelgin HV)

~~Obtained~~The obtained coating for an undercoating layer is coated ~~te~~onto one surface of a substrate (paper of 60g/m<sup>2</sup>)

using a blade coater, then dried ~~up~~ and an undercoating layer of a coating amount of 10.0 g/m<sup>2</sup> is obtained.

Dispersions of the following blending ratio for each ~~material~~ material for ~~color-developing~~ a color-developing agent (A solution) and basic leuco dye (B solution) are prepared, and are ground separately in a wet condition by using a sand grinder to an average particle size of 1 $\mu$ m.

A solution (dispersion of color developing agent)

4-hydroxy-4'-isopropoxydiphenylsulfone	6.0 parts
10% aqueous solution of polyvinyl alcohol	18.8 parts
water	11.2 parts

B solution (dispersion of basic leuco dye)

3-dibutylamino-6-methyl-7-anilino fluorane	2.0 parts
10% aqueous solution of polyvinyl alcohol	4.6 parts
water	2.6 parts

Then these dispersions are mixed by the following ratio and a coating for recording layer is prepared

Coating liquid for a recording layer

A solution (dispersion of

color--developing agent) 36.0 parts

B solution (dispersion of basic leuco dye) 9.2 parts

Kaolin clay (50% dispersion) 12.0 parts

Then the obtained coating liquid for the recording layer is coated on the undercoating layer ~~of said undercoated layer~~ by a blade coater so ~~as that~~ the coating quantity to be is 4g/m<sup>2</sup> and dried ~~up~~. This sheet is treated by a super calendar so ~~as that~~ the smoothness to be 500-600 sec and a thermally sensitive recording medium is obtained.

#### Example 2

By the same process ~~as~~ Example 1, except for coating the recording layer on the undercoating layer of said undercoating layer forming paper by a curtain coater instead of a blade coater, a thermally sensitive recording medium is obtained.

## Example 3, Example 4

By the same process ~~to~~as Example 1, except for adjusting ~~solid~~the solids concentration and dynamic water-retention capacity of the coating for the undercoating layer as shown in Table 1, a thermally sensitive recording medium is obtained.

## Example 5

By the same process ~~to~~as Example 1, except for changing the blending ratio of 2% aqueous solution of sodium alginate of U solution (coating for undercoating layer) to 2.5 parts, a thermally sensitive recording medium is obtained.

## Example 6

By the same process ~~to~~as Example 1, except for changing the blending ratio of 2% aqueous solution of sodium alginate of U solution (coating for undercoating layer), a thermally sensitive recording medium is obtained.

## Comparative Example 1

By the same process ~~to~~as Example 1, except for not blending 2% aqueous solution of sodium alginate in preparation of U solution (coating for undercoating layer), a thermally sensitive recording medium is obtained.

## Comparative Example 2, Comparative Example 3

By the same process ~~to~~as Example 1, except for adjusting ~~solid~~the solids concentration and dynamic water-retention capacity of the coating for the undercoating layer as ~~to~~ shown in Table 2, a thermally sensitive recording medium is obtained.

In Comparative Example 2, sodium alginate whose viscosity of 1% aqueous solution is 40-80mPa·s (product of Kelco Co., Ltd., commodity name; Kelgin LV) is used as sodium alginate.

Further, in Comparative Example 3, precipitated calcium carbonate (product of Shiraishi Kogyo Co., Ltd., commodity



name; Brilliant 15, ~~oil-absorbing~~oil-absorbing capacity ~~is at~~  
43cc/100g) is used.

<Evaluation of color developing sensitivity>

Prepared specimens of a thermally sensitive recording medium are subjected to printing at an applied energy of 0.344 mJ/dot by using TH-PMD (printing test machine for thermally sensitive recording paper, thermal head of Kyocera Co., Ltd is installed) product of Okura Denki Co., Ltd. ~~Image~~The image densities of the recorded part are measured and evaluated by using a Macbeth Densitometer (RD-18i).

<Evaluation of printed image>

Printed part is evaluated by visual inspection.

○: white spots ~~is~~are not observed

△: white spots are observed

×: many spots are observed

<Evaluation of coating aptitude>

The coating ~~runability~~runability and the obtained coated surface are evaluated.

○: coating can be done without any problem, and the condition of coated surface by visual inspection is good.

△: coating can be done without big ~~problem~~problems, however, sometimes, ~~problem~~problems like ~~streak~~streaking or ~~stain~~staining of a roller are observed, and long term stable coating is difficult.

×: coating defects such as ~~streak causes at~~streaking during the coating process and stable coating is impossible.

<Measuring method of dynamic water-retention capacity>

Dynamic water-retention capacity is measured by Water Retention Meter, product of Kaltec Scientific Co., Ltd., using a specified film (filter) "AA- GWR Test Filters (KALTEC SCIENCE, Inc.), GWR420" and a filtering paper "Whatmans Chromatography 17". When this value is small, it

~~ndicate~~indicates a high dynamic water-retention capacity and a high water-retention ability ~~of~~-right under a blade, and defects such as ~~streak~~streaking are not caused easily on a coated surface.

Table 1

	No.	Example					
		1	2	3	4	5	6
undercoating layer	pigment	calcined clay	calcined clay	calcined clay	calcined clay	calcined clay	calcined clay
	water retention agent (name) contents *	sodium algininate Kelgin HV 0.1	sodium algininate Kelgin HV 0.1	sodium algininate Kelgin HV 0.1	sodium algininate Kelgin HV 0.1	sodium algininate Kelgin HV 0.05	sodium algininate Kelgin HV 1.2
	conc. of solid of a coating %	38	38	35	32	38	38
	dynamic water-retention capacity	280	280	323	342	330	270
	B viscosity mPa·s	1340	1340	580	340	960	1360
	high shear viscosity mPa·s	46	46	36	29	47	44
thermally sensitive layer	coating method	blade	curtain	blade	blade	blade	blade
quality	sensitivity	O 1.33	O 1.34	O 1.33	O 1.32	O 1.32	Δ 1.24
	Printed image	O	●	O	Δ	Δ	O
coating aptitude	undercoating layer	O	O	O	O	O	O

\* parts (weight parts) to 100 weight parts to pigment

Table 2

	No,	Comparative Example		
		1	2	3
undercoating layer	pigment	calcined clay	calcined clay	calcined clay
	water retention agent (name) contents	no	sodium alginate Kelgin LV 0.1	sodium alginate Kelgin HV 0.1
	conc. of solid of a coating %	38	38	38
	dynamic water-retention capacity	420	390	200
thermally sensitive layer	B viscosity mPa·s	750	880	560
	high shear viscosity mPa·s	47	45	17
	coating method	blade	blade	blade
	sensitivity	O 1.35	O 1.32	x 1.09
coating aptitude	printed image	x	x	Δ
	undercoating layer	Δ	Δ	O

## INDUSTRIAL APPLICABILITY

According to the present invention, a thermally sensitive recording medium which has a high recording sensitivity and superior ~~in~~-printing image can be obtained by containing a water-retention agent, in particular, sodium alginate in an undercoating layer.